



ECO- MASTIC CORK FILLED

55-61

COLOR

Gray

SERVICE TEMPERATURE

0 to 180° F
(17.8 to 82°C)

COVERAGE

The coverage is dependent on the surface being covered and the application method.

1/8" wet film = 8 gal./100 sq. ft.

1/4" wet film = 16 gal./100 sq. ft.

WEIGHT PER GALLON

7.7 lbs.

AVERAGE NONVOLATILE

66% by weight

DRYING TIME

8 gal./100 sq.ft.:Touch: 2 hrs.

Through: 48 hours

The drying time depends on the temperature, humidity and film thickness.

SAFETY

Flammability:

Wet: Non-flammable

Dry: Fire resistive

ASBESTOS FREE

CAUTION:

Water-based product. Do not freeze. Use with Adequate Ventilation. Avoid prolonged or repeated breathing of vapor. Avoid prolonged or repeated contact with skin. Do not take internally. In an emergency, call a physician. Keep out of reach of children.

WARRANTY TERMS: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. **WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE.** No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

DESCRIPTION

55-61 Eco- Mastic Cork Filled is a mastic containing a blend of granulated cork. It is designed to provide some condensation control and insulation value where conditions are not too severe. It may be used on tanks and piping where standard insulation isn't practical.

LIMITATIONS

Do not apply below 40° F (4.4°C) and 100°F (38°C)
Keep from freezing.

METHOD OF APPLICATION

Glove, spray.

MATERIAL PREPARATION

Do not thin. Stir well.

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople. Be sure surfaces are clean and dry. Prime steel surfaces with a flat corrosion-inhibitive primer. For best results build up thickness with multiple coats allowing 24 hours drying between. However, 1/4" wet film can be applied in one coat.

Trowel or glove in even strokes to prevent excessive working of material.

Spray apply using air atomizing mastic spray equipment.

CLEANUP

Water

VOC = 0.28 lbs./gal or 34 grams/liter. Less water & exempt solvents.

rev. 07/2017

MON-ECO INDUSTRIES, INC.

5 JOANNA COURT • EAST BRUNSWICK, NJ 08816
(732) 257-7942 • 800-899-6326 • FAX (732) 257-6525

www.mon-ecoindustries.com



HEATING, AIRCONDITIONING & REFRIGERATION DISTRIBUTORS INTERNATIONAL