



FABRICATION ADHESIVE

88-70

COLOR

White

SERVICE TEMPERATURE

-10°F TO 200° F

COVERAGE

300 to 400 sq. ft./gal.

The coverage rate is dependent on the surface being covered and the application method.

WEIGHT PER GALLON

8.9 lb.

AVERAGE NONVOLATILE

74% by weight

BONDING TIME

0 to 12 minutes

The bonding time depends on the temperature, humidity and film thickness.

SAFETY

Wet: Non-flammable

LIMITATIONS

Keep from freezing.

Apply between 50°F (10°C) and 110°F (43°C)

Cold temperatures extend tack time.

CAUTION

This is a water based adhesive, but use with adequate ventilation to avoid prolonged breathing of vapors. We know of no harmful effects, but some may become upset by mild odor. Avoid prolonged or repeated contact with skin. Irritation could result. Wash with soap and water. Avoid contact with eyes. If splashed in eyes, flush with clean water to remove. If irritation results, consult a physician. Keep out of reach of children.

DESCRIPTION

88-70 is a non-flammable, water-based adhesive. It is ideal for Pipe & Tank laminates. It can be used with fiberglass, mineral wool and foamboard systems.

METHOD OF APPLICATION

Brush, spray or roller.

MATERIAL PREPARATION

Do not thin. Ready to use.

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople.

CLEANUP

Wet: Water, Dry: Trichloroethylene or MEI 44-10

ASBESTOS FREE

VOC= 0.02 lbs/gal or 2.6 grams/liter. Less water & exempt solvents.

rev. 07/2017

WARRANTY TERMS: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE. No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

Mon-Eco Industries, Inc.

5 JOANNA COURT • EAST BRUNSWICK, NJ 08816
(732) 257-7942 • 800-899-6326 • FAX (732) 257-6525

www.mon-ecoindustries.com



HEATING, AIRCONDITIONING & REFRIGERATION DISTRIBUTORS INTERNATIONAL